

Technical Data Sheet

Product Name: Alumina Grinding Media
Catalog No.: AC3939 (Wet Grinding), AC3938 (Dry Grinding)
Composition: Al₂O₃
Dimensions: φ0.5 mm to φ90 mm, or Customized
Shape: Ball, Bead



Specification

Type	AGBD75	AGBD92	AGBD95	AGBD99
Al ₂ O ₃ (%)	≥75	≥92	≥95	≥99
Bulk Density (g/cm ³)	>3.20	>3.60	>3.65	≥3.68
Hardness (Mohs)	7.5	9	9	9
Wear Loss (%)	<0.015	<0.015	<0.012	<0.01
Size	φ0.5 mm to φ90 mm (or customized)			

The above products are available with purity up to 99.9% or even 99.99%, and sizes can be customized upon request. Please contact us for more details.

Stanford Advanced Materials

By..... *Wouman*